

CONVENTIONAL MOSFET

FIG. 1
(PRIOR ART)


20
16
12
8
4
0
R_{on} x A
[Ωmm²]
0
200
400
600
800
1000
BREAKDOWN VOLTAGE $V_{(BR)DSS}$ [V]
20
25

FIG. 2



THE DOPANT DISTRIBUTION OF A HIGH VOLTAGE VERTICAL DMOS TRANSISTOR WITH A RELATIVELY LOW ON-RESISTANCE

FIG. 3

1. EPITAXIAL DEPOSITION
2. FORMATION OF THE TRENCH ETCH STOP LAYER
3. MASK AND ETCH THE TRENCH ETCH STOP LAYER
4. TRENCH ETCH



FIG. 4(a)

5. GROW THIN OXIDE LAYER IN THE TRENCH
6. IMPLANT THE DOPANT



FIG. 4(b)

7. PERFORM A HIGH TEMPERATURE DIFFUSION
8. ETCH THE OXIDE AT THE BOTTOM OF THE TRENCH



FIG. 4(c)

9. REPEAT THE DOPING AND ETCH STEPS AS MANY TIMES AS REQUIRED

10. DOPE THE REGION FURTHEST FROM THE SURFACE



FIG. 4(d)

11. FILL THE TRENCH

12. PLANARIZE THE WAFER SURFACE



FIG. 4(e)

13. PERFORM A HIGH TEMPERATURE DIFFUSION STEP



FIG. 4(f)